


N71-30938
NASA CR-119242



**CASE FILE
COPY**

EVALUATION PROGRAM

for

SECONDARY SPACECRAFT CELLS

ACCEPTANCE TEST
OF

GENERAL ELECTRIC COMPANY

6.0 AMPERE-HOUR NICKEL-CADMIUM CELLS
W/ SIGNAL & RECOMBINATION ELECTRODES

prepared for
GODDARD SPACE FLIGHT CENTER
CONTRACT W12,397

QUALITY EVALUATION LABORATORY

NAD CRANE, INDIANA

DEPARTMENT OF THE NAVY
NAVAL AMMUNITION DEPOT
CRANE, INDIANA 47522

IN REPLY REFER TO:
3022-DEC:mm
8900

29 JUN 1971

From: Commanding Officer, Naval Ammunition Depot, Crane, Indiana
To: National Aeronautics and Space Administration, Goddard Space Flight
Center (761.2, Mr. T. J. Hennigan), Greenbelt, Maryland 20771

Subj: Report QE/C 71-187; Acceptance Test of General Electric Company
6.0 Ampere-Hour Nickel-Cadmium Secondary Spacecraft Cells with
Signal and Recombination Electrodes

Ref: (a) NASA Purchase Order W12,397

Encl: (1) Report QE/C 71-187

1. In compliance with reference (a), enclosure (1) is forwarded for
information and retention.


C. G. LYNCH
By direction

Copy to:
Distribution List

NAVAL AMMUNITION DEPOT
QUALITY EVALUATION DEPARTMENT
CRANE, INDIANA 47522

EVALUATION PROGRAM
FOR
SECONDARY SPACECRAFT CELLS

ACCEPTANCE TEST
OF
GENERAL ELECTRIC COMPANY
6.0 AMPERE-HOUR
NICKEL-CADMIUM CELLS

QE/C 71-187

1 JUNE 1971

PREPARED BY

D. E. Christy

D. E. CHRISTY

PREPARED UNDER THE DIRECTION OF

Harold Forston

HAROLD FORSTON
Acting Manager, Electrochemical
Power Sources Branch

APPROVED BY

C. G. Lynch
C. G. LYNCH
By direction

Enclosure (1)

REPORT BRIEF
6.0 AMPERE-HOUR NICKEL-CADMIUM
SECONDARY SPACECRAFT CELLS
WITH SIGNAL AND RECOMBINATION ELECTRODES
MANUFACTURED BY GENERAL ELECTRIC COMPANY

Ref: (a) NASA Purchase Order W12,397
(b) NAD Crane Test Procedure 3052-TP 304, Rev A

I. TEST ASSIGNMENT BRIEF

A. The purpose of this acceptance test is to provide a "base line" reference, prior to life cycling, for new cells. It also provides a screening against cells that are obviously bad due to internal shorts or gross leakage. The reference is provided with regard to physical dimensions, electrolyte leakage, cell capacity, internal shorts, ability to withstand long periods of overcharge, and internal resistance measurements. All cells complete the entire series of tests. Cells are removed from individual segments of the test only if pressure or voltage limits are reached and cell damage would result from further testing during that segment.

B. The 25 cells were purchased from General Electric Company of Gainesville, Florida by the National Aeronautics and Space Administration (NASA). These cells were rated at 6.0 ampere-hours by the manufacturer. In addition to the positive and negative terminals, they have a signal electrode and a recombination electrode. Testing on these cells was funded in accordance with reference (a).

II. SUMMARY OF RESULTS

A. The overall averages for the three capacity checks were respectively, 7.26, 7.01 and 6.82 ampere-hours.

B. The cells averaged 1.218 volts after 24 hours of open circuit during which they recovered from a dead short. These results indicate that no internal shorts existed.

C. Five of the 25 cells had to be removed from the c/10 overcharge due to high cell voltage. The time-on-charge at this rate varied from 5 to 14 hours (see Table I).

D. Internal resistance was measured across the cell terminals, the signal electrodes, and the recombination electrodes. The average resistances are: cell, 2.85 milliohms; signal electrode, 52.0 milliohms; and recombination electrode, 71.2 milliohms.

E. Eleven of the 25 cells showed electrolyte leakage during one or more of the three leak tests. A summary of these tests is found in Table I.

RESULTS OF ACCEPTANCE TESTS
OF
6.0 AMPERE-HOUR NICKEL-CADMIUM
SECONDARY SPACECRAFT CELLS
WITH SIGNAL AND RECOMBINATION ELECTRODES
MANUFACTURED BY GENERAL ELECTRIC COMPANY

I. INTRODUCTION

A. On 2 December 1970, testing was begun on 25 cells in accordance with reference (b). These tests were completed on 19 January 1971. Table I summarizes the results.

II. TEST CONDITIONS

A. All acceptance tests were performed at an ambient temperature between 23° C and 27° C at existing relative humidity and atmospheric pressure, and consisted of the following:

1. Physical measurement.
2. Three capacity tests.
3. Cell short test.
4. Overcharge tests at c/20 and c/10.
5. Internal resistance tests of cell, signal electrode and recombination electrode.
6. Three leak tests: initial, after capacity tests, and after overcharge tests.

B. Appendix I gives the details of the test procedure.

III. CELL IDENTIFICATION AND DESCRIPTION

A. The cells were identified by the manufacturer's catalog number, 42B006AB29. They were placed into packs according to the manufacturer's serial numbers. Table II lists these numbers along with the physical dimensions and cell weights.

B. These cells are rectangular with a stainless steel cell cover and container. Both terminals are insulated from the cell cover by ceramic seals and protrude through the cover as solder type terminals. The signal electrode, which is used for charge control, is welded to a wire that protrudes through a hole in the cell cover. This hole is potted to seal the cell. The recombination electrode is welded to the inside of the container, and its terminal is a stainless steel tab welded to the outside.

IV. RESULTS--The following data was condensed from Table I.

A. Capacity Tests:

1. The capacities of all 25 cells exceeded the manufacturer's rated capacity--ranging from 6.40 to 7.59 ampere-hours. The average capacity for the three respective capacity tests were 7.26, 7.01 and 6.82 ampere-hours.

B. Cell Short Test:

1. All cells indicated they were free of internal shorts by recovering, in excess of 1.150 volts, during a 24-hour open circuit period following a dead short across the terminals. The open circuit voltages ranged from 1.171 to 1.228 volts, averaging 1.218 volts.

C. Overcharge Test:

1. Five cells had to be removed from the c/10 overcharge due to high cell voltage--exceeding 1.500 volts. The time-on-charge at the c/10 rate varied from 5 to 14 hours for these five cells.

D. Internal Resistance:

1. Internal resistance was measured across the cell terminals, across the signal electrode (from signal electrode terminal to negative terminal), and across the recombination electrode (from recombination electrode terminal to negative terminal). All values were consistent for a given set of measurements. The resistances across the cell terminals ranged from 2.67 to 3.21 milliohms, averaging 2.85 milliohms. The resistances across the signal electrodes ranged from 43.0 to 68.0 milliohms, averaging 52.0 milliohms. The resistances across the recombination electrodes ranged from 47.5 to 122.0 milliohms, averaging 71.2 milliohms.

E. Leak Tests:

1. Eleven of the 25 cells showed electrolyte leakage during one or more of the three leak tests. The leakage was more prevalent .

around the positive terminal and the signal electrode terminal. Most leakage was slight and discovered following the capacity tests and/or the overcharge tests.

TABLE I

CAPACITY CHECKS

Serial Number	Amperes- Hours	END OF DISCHARGE			Vacuum Inches Hg.	END OF CHARGE			Amperes- Hours	END OF CHARGE			Vacuum Inches Hg.
		Signal Electr Voltage	Recomb Electr Voltage	Electr Voltage		Signal Electr Voltage	Recomb Electr Voltage	Electr Voltage		Signal Electr Voltage	Recomb Electr Voltage	Electr Voltage	
002	7.30	-0.014	-0.022	-0.022	21	-0.022	-0.030	-0.030	7.20	-0.022	-0.030	-0.030	21
003	7.30	-0.039	-0.026	-0.026	20	-0.027	-0.030	-0.030	7.26	-0.027	-0.030	-0.030	21
004	7.14	-0.041	-0.007	-0.007	21	-0.012	-0.014	-0.014	6.99	-0.012	-0.014	-0.014	26
005	7.25	-0.043	-0.031	-0.031	18	-0.044	-0.015	-0.015	6.99	-0.044	-0.015	-0.015	19
006	7.25	-0.056	-0.036	-0.036	19	-0.011	-0.006	-0.006	6.96	-0.011	-0.006	-0.006	20
Pack Avg.	7.25								7.08				
007	7.50	-0.051	-0.031	-0.031	22	-0.007	-0.024	-0.024	7.41	-0.007	-0.024	-0.024	22
008	7.50	+0.278	+0.861	+0.861	19	+0.474	+0.892	+0.892	7.29	+0.474	+0.892	+0.892	4
009	7.26	-0.042	-0.044	-0.044	28	-0.019	-0.037	-0.037	6.81	-0.019	-0.037	-0.037	28
011	7.20	-0.014	-0.035	-0.035	25	-0.004	-0.032	-0.032	6.84	-0.004	-0.032	-0.032	27
013	7.29	-0.018	-0.054	-0.054	15	-0.015	-0.029	-0.029	6.96	-0.015	-0.029	-0.029	15
Pack Avg.	7.35								7.06				
014	7.59	-0.060	-0.042	-0.042	29	+0.003	-0.013	-0.013	7.26	+0.003	-0.013	-0.013	21
015	7.59	-0.012	-0.050	-0.050	9	-0.007	-0.017	-0.017	7.26	-0.007	-0.017	-0.017	10
016	7.29	-0.027	-0.037	-0.037	27	-0.022	-0.023	-0.023	6.99	-0.022	-0.023	-0.023	26
018	7.35	-0.019	-0.046	-0.046	21	-0.018	-0.037	-0.037	7.11	-0.018	-0.037	-0.037	21
019	7.56	-0.021	-0.046	-0.046	23	-0.018	-0.026	-0.026	7.14	-0.018	-0.026	-0.026	22
Pack Avg.	7.48								7.15				
020	7.14	-0.014	-0.057	-0.057	25	-0.014	-0.027	-0.027	7.05	-0.014	-0.027	-0.027	21
021	7.29	-0.046	-0.040	-0.040	25	-0.011	-0.019	-0.019	7.29	-0.011	-0.019	-0.019	23
022	7.26	-0.020	-0.044	-0.044	19	-0.018	+0.026	+0.026	7.14	-0.018	+0.026	+0.026	17
023	7.11	-0.020	-0.048	-0.048	20	-0.017	-0.036	-0.036	6.99	-0.017	-0.036	-0.036	21
025	7.14	-0.019	-0.049	-0.049	10	-0.009	-0.027	-0.027	7.14	-0.009	-0.027	-0.027	10
Pack Avg.	7.19								7.12				
047	7.14	-0.028	-0.034	-0.034	21	0.006	-0.025	-0.025	6.85	0.006	-0.025	-0.025	22
050	7.20	-0.020	-0.025	-0.025	31	0.003	-0.022	-0.022	6.85	0.003	-0.022	-0.022	30
066	6.85	-0.012	-0.019	-0.019	26	-0.007	-0.029	-0.029	6.40	-0.007	-0.029	-0.029	24
067	7.00	-0.021	-0.035	-0.035	22	-0.018	-0.035	-0.035	6.65	-0.018	-0.035	-0.035	21
068	6.90	-0.023	-0.037	-0.037	21	-0.018	-0.035	-0.035	6.45	-0.018	-0.035	-0.035	20
Pack Avg.	7.02								6.64				
Overall Avg	7.26								7.01				
									6.82				

TABLE I (Cont.)

Cell Short Test Serial Number	Volts*	END OF c/20 OVERCHARGE				END OF c/10 OVERCHARGE				INTERNAL RESISTANCE TEST (milliohms)			
		Signal		Recomb		Signal		Recomb		Cell	Signal	Electr	Recomb
		Electr	Electr	Electr	Electr	Electr	Electr	Electr	Electr				
002	1.202	1.472	0.451	0.449	0.449	1.484	0.518	0.605	3	2.76	43.0	53.8	
003	1.208	1.484	0.372	0.408	0.408	1.496	0.461	0.506	-1	2.83	47.8	56.5	
004	1.208	1.488	0.398	0.452	0.452	1.495	0.467	0.502	9	2.84	50.8	60.2	
005	1.205	1.472	0.386	0.505	0.505	1.471	0.397	0.574	-8	2.72	45.0	77.5	
006	1.204	1.480	0.430	0.459	0.459	1.515c	0.474	0.399	+47	2.71	46.0	70.0	
Pack Avg	1.205									2.77	46.5	63.6	
007	1.212	1.451	0.361	0.320	0.320	1.504d	0.520	0.462	39	2.67	45.9	84.1	
008	1.214	1.439	0.355	0.404	0.404	1.503d	0.550	0.639	11	2.74	58.0	60.1	
009	1.229	1.428	0.251	0.389	0.389	1.460	0.362	0.782	-18	2.82	45.4	77.3	
011	1.210	1.432	0.318	0.407	0.407	1.461	0.385	0.779	10	2.71	50.2	86.2	
013	1.221	1.441	0.283	0.341	0.341	1.474	0.414	0.673	1	2.68	44.1	83.9	
Pack Avg	1.217									2.72	48.7	71.7	
014	1.217	1.439	0.358	0.317	0.317	1.47	0.531	0.571	5	2.80	51.0	59.5	
015	1.171	1.488	0.351	0.182	0.182	1.521a	0.495	0.251	51	2.89	53.9	96.3	
016	1.202	1.436	0.243	0.393	0.393	1.491	0.440	0.688	3	2.96	48.8	75.8	
018	1.176	1.460	0.269	0.343	0.343	1.526	0.406	0.415	20	2.71	45.0	89.0	
019	1.198	1.482	0.273	0.270	0.270	1.532b	0.448	0.214	52	2.69	50.0	68.3	
Pack Avg	1.193									2.81	49.7	77.8	
020	1.228	1.474	0.352	0.242	0.242	1.502	0.003	0.222	35	2.71	67.5	60.2	
021	1.206	1.447	0.367	0.321	0.321	1.470	0.451	0.626	-2	2.83	49.9	67.0	
022	1.233	1.448	0.342	0.261	0.261	1.488	0.540	0.475	11	2.80	48.0	69.1	
023	1.227	1.444	0.213	0.316	0.316	1.473	0.408	0.597	8	2.79	51.2	87.0	
025	1.219	1.447	0.198	0.264	0.264	1.467	0.354	0.529	0	2.77	51.9	122.0	
Pack Avg	1.223									2.78	54.3	81.1	
047	1.218	1.451	0.292	0.248	0.248	1.505	0.309	0.244	8	3.21	68.0	47.5	
050	1.205	1.439	0.306	0.293	0.293	1.479	0.415	0.586	-20	3.15	46.2	54.0	
066	1.225	1.491	0.249	0.104	0.104	1.521	0.388	0.074	41	3.07	72.5	73.0	
067	1.218	1.472	0.239	0.287	0.287	1.526	0.393	0.080	36	3.15	57.0	79.0	
068	1.225	1.461	0.233	0.312	0.312	1.519	0.166	0.175	36	3.15	60.2	56.0	
Pack Avg	1.218									3.17	60.8	61.9	
Overall Avg	1.218									2.85	52.0	71.2	

a out after 5 hours at c/10 due to high cell voltage
b out after 6 hours at c/10 due to high cell voltage
c out after 11 hours at c/10 due to high cell voltage
d out after 14 hours at c/10 due to high cell voltage
*24-Hour Recovery from dead short

**Negative gauge pressures are automatically interpreted as inches of mercury vacuum

TABLE I (Cont)

LEAK TEST

SERIAL NUMBER	NO LEAKS	+ POST	- POST	FILL TUBE	SIGNAL ELECTRODE
002	X				
003	X				
004	X				
005	X				
006	X				
007	X				
008		V.S.(1)			
009					
011			V.S.(2)	V.S.(1)	V.S.(1) V.S.(1)
013	X				
014	X				
015		V.S.(2,3)c			V.S.(2,3)
016	X				
018	X				V.S.(2,3)
019					
020		V.S.(1)			V.S.(2)
021	X				
022	X				
023	X				
025		L(2)			L(2,3)
047		V.S.(2)		V.S.(2)	V.S.(1,2)
050		V.S.(2)			
066	X				
067				V.S.(1) V.S.(1), L(2)	V.S.(1,2) V.S.(1), L(2)
068		L(2)	L(2)		

X= no leaks V.S.=very slight leak L=strong indication of leakage
 (1) initial leak test (2) leak test following capacity checks (3) leak test following overcharge

TABLE II

CELL SERIAL NO.	WEIGHT GRAMS	HEIGHT INCHES	LENGTH INCHES	WIDTH - INCHES
002	568.3	3.565	0.839	2.132
003	569.1	3.561	0.865	2.132
004	570.6	3.563	0.838	2.138
005	566.2	3.561	0.832	2.131
006	699.7	3.561	0.930	2.160
007	556.5	3.569	0.831	2.139
008	552.1	3.563	0.831	2.135
009	566.6	3.561	0.838	2.132
011	566.9	3.559	0.835	2.136
013	565.2	3.561	0.838	2.131
014	574.2	3.569	0.861	2.132
015	568.1	3.569	0.835	2.160
016	568.1	3.560	0.832	2.160
018	565.8	3.562	0.862	2.131
019	572.1	3.568	0.809	2.131
020	570.2	3.590	0.839	2.131
021	569.9	3.591	0.831	2.132
022	571.3	3.561	0.838	2.131
023	569.5	3.591	0.837	2.165
025	566.9	3.569	0.839	2.131
047	573.1	3.569	0.839	2.131
050	566.3	3.599	0.839	2.131
066	568.3	3.600	0.831	2.131
067	568.4	3.599	0.867	2.131
068	568.5	3.601	0.862	2.139
AVG	566.5		0.840	

QE/C 71-187

APPENDIX I

I. TEST PROCEDURE

A. Phenolphthalein Leak Test:

1. The phenolphthalein leak test is a determination of the condition of the welds and ceramic seals on receipt of the cells. This test was performed prior to any other tests, with a phenolphthalein spray indicator solution of one-half of one percent concentration.

B. Capacity Tests:

1. The capacity test is a determination of the cell capacity at the $c/2$ discharge rate, where c is the manufacturer's rated capacity to a cutoff voltage of 1.00 volt per cell. The discharge was made after a 1-hour open circuit period following the 16-hour charge at the $c/10$ rate. A total of three capacity checks was made at this activity. The cells were discharged individually, but were recharged in series.

2. The signal electrodes were loaded with 330-ohm resistors and the recombination electrodes were loaded with 2.2-ohm resistors. These resistors were installed prior to the start of the capacity checks and remained throughout the test.

C. Cell Short Test:

1. The cell short test is a means of detecting slight shorting conditions which may exist because of imperfections in the insulating materials, or damage to element in handling or assembly.

2. Following completion of the third capacity discharge test, each cell was loaded with a 0.5-ohm, 3-watt resistor and allowed to stand 16 hours with the resistor acting as a shorting device. At the end of 16 hours, the resistors were removed and the cells were placed on open circuit stand for 24 hours. Any cell whose voltage did not recover to 1.15 volts or higher was considered as failing this portion of the acceptance test.

D. Leak Test:

1. The leak test is a means of detecting leakage of a seal or weld. The test was performed before and after the overcharge test sequence to determine the presence of leaks.

2. The cells were placed in a vacuum chamber and exposed to a vacuum of 40 microns of mercury or less for 24 hours. The cells were then removed from the vacuum chamber and sprayed with phenolphthalein. Faintly pink areas were designed as slight leakers. Darker, more obvious, discolorations of pink or red were noted as definite leakers.

E. Overcharge Test:

1. The purpose of this test is basically twofold:

a. To determine the degree to which a pack of cells maintain a balanced voltage.

b. To determine the cells capability of reaching a point of chemical equilibrium--oxygen recombination with the recombination electrode to control pressure.

2. The overcharge tests were performed to determine the steady state voltage at specified rates. The test specified a series of constant current charges at $c/10$, $c/20$ and $c/10$ for a minimum of 16 hours at each charge rate. The first $c/10$ rate serves to establish a condition of overcharge.

3. The cells were monitored hourly throughout the test. Charging was to be discontinued on cells which exceeded 1.50 volts.

F. Internal Resistance Test:

1. Immediately following the overcharge test, the internal resistance was measured across the cell terminals, across the signal electrode (from signal electrode terminal to negative terminal), and across the recombination electrode (from recombination electrode terminal to negative terminal). The measurements were made with a Hewlett-Packard milliohmmeter (Model 4328A).

G. Leak Test:

1. Following the internal resistance measurements, the cells were still in a charged state. The cells were discharged at $c/2$ to 0.00 volt and shorted prior to the final leak test. The shorted cells were then placed in a vacuum chamber and the procedure described in paragraph I.D.2. was repeated.

DISTRIBUTION LIST

National Aeronautics and Space Administration, Goddard Space Flight Center (Code 761.2, Mr. T. J. Hennigan), Greenbelt, Maryland 20771 (12 copies)

National Aeronautics and Space Administration (Code RNW, Mr. Ernst M. Cohn), Washington, D. C. 20546

National Aeronautics and Space Administration (Code SCC, Mr. A. M. Greg Andrus), Washington, D. C. 20546

National Aeronautics and Space Administration, Scientific and Technical Information Center; Input, P. O. Box 33, College Park, Maryland 20740 (3 copies)

National Aeronautics and Space Administration (Code UT, Dr. E. N. Case), Washington, D. C. 20546

National Aeronautics and Space Administration (Code MTG, Mr. Richard Livingston), Washington, D. C. 20546

National Aeronautics and Space Administration, Goddard Space Flight Center (Code 734, Mr. Joseph Sherfey), Greenbelt, Maryland 20771

National Aeronautics and Space Administration, Goddard Space Flight Center (Code 734, Mr. Gerald Halpert), Greenbelt, Maryland 20771

National Aeronautics and Space Administration, Goddard Space Flight Center (Code 450, Mr. Louis Wilson), Greenbelt, Maryland 20771

National Aeronautics and Space Administration, Langley Research Center (MS-472, Mr. John L. Patterson), Hampton, Virginia 23365

National Aeronautics and Space Administration, Langley Research Center (MS-488, Mr. Jack E. Zanks), Hampton, Virginia 23365

National Aeronautics and Space Administration, Lewis Research Center (MS 302-1, Dr. Louis Rosenblum), 21000 Brookpark Road, Cleveland, Ohio 44135

National Aeronautics and Space Administration, Lewis Research Center (MS 309-1, Mr. Harvey Schwartz), 21000 Brookpark Road, Cleveland, Ohio 44135

National Aeronautics and Space Administration, Lewis Research Center
(MS 309-1, Dr. J. Stewart Fordyce), 21000 Brookpark Road, Cleveland,
Ohio 44135

National Aeronautics and Space Administration, George C. Marshall
Space Flight Center (S&E-ASTR-EP, Mr. Charles B. Graff), Huntsville,
Alabama 35812

National Aeronautics and Space Administration, Manned Spacecraft
Center (EP-5, Mr. W. E. Rice), Houston, Texas 77058

National Aeronautics and Space Administration, Ames Research Center
(M.S. 244-2, PBS, Mr. Jon A. Rubenzer), Moffett Field, California 94035

Jet Propulsion Laboratory (M.S. 198-220, Mr. Daniel Runkle),
4800 Oak Grove Drive, Pasadena, California 91103

Jet Propulsion Laboratory (M.S. 198-220, Mr. Alvin A. Uchiyama),
4800 Oak Grove Drive, Pasadena, California 91103

Jet Propulsion Laboratory (M.S. 198-220, Dr. R. Lutwack),
4800 Oak Grove Drive, Pasadena, California 91103

Commanding General, U. S. Army Electro Technology Lab, Energy
Conversion Research Division (MERDC), Fort Belvoir, Virginia 22060

Commanding General, U. S. Army Electronics R&D Labs (AMSEL-KL-P),
Fort Monmouth, New Jersey 07703

Commanding General, U. S. Army Electronics Command (AMSEL-ME-NMP-TB-2,
Mr. A. Frink), Fort Monmouth, New Jersey 07703

U. S. Army Natick Laboratories, Clothing and Organic Materials
Division (Mr. Leo A. Spano), Natick, Massachusetts 01762

Harry Diamond Laboratories (Mr. Nathan Kaplan), Room 300, Building 92,
Connecticut Ave. & Van Ness Street, N.W., Washington, D. C. 20438

Chief of Naval Research (Code 473, Director, Power Program),
Department of the Navy, Arlington, Virginia 22217

Chief of Naval Research (Code 472, Mr. Harry Fox), Department of
the Navy, Arlington, Virginia 22217

Director, Naval Research Laboratory (Code 6160, Dr. J. C. White),
4555 Overlook Avenue, S.W., Washington, D. C. 20360

Officer In Charge, Annapolis Division, Naval Ship Research &
Development Center (Code A731, Mr. J. H. Harrison), Annapolis,
Maryland 21402

Commander, Naval Air Systems Command (AIR-340C, Mr. Milton Knight),
Department of the Navy, Washington, D. C. 20360

Commander, Naval Ordnance Laboratory, White Oak (Code 232,
Mr. Philip B. Cole), Silver Spring, Maryland 20910

Commander, Naval Ship Engineering Center (Code 6157C, Mr. C. F.
Viglotti), Center Building, Prince George Center, Hyattsville,
Maryland 20782

Commander, Naval Ship Engineering Center (Code 6157D, Mr. Albert
Himy), Center Building, Prince George Center, Hyattsville,
Maryland 20782

Superintendent, Naval Observatory (STIC, Mr. Robert E. Trumbule),
4301 Suitland Road, Suitland, Maryland 20390

Commander, Naval Ship Systems Command (SHIP-03422, Mr. Bernard B.
Rosenbaum), Department of the Navy, Washington, D. C. 20360

Department of the Air Force Headquarters, Aero Propulsion
Laboratory (APIP-1, Mr. James E. Cooper), Wright-Patterson Air
Force Base, Ohio 45433

Air Force Cambridge Research Laboratory (CREC, Mr. Edward Raskind,
Wing F), L. G. Hanscom Field, Bedford, Massachusetts 01731

Rome Air Development Center (Code EMRED, Mr. Frank J. Mollura),
Griffiss Air Force Base, New York 13442

Headquarters, SAMS0 (SMTAE, Lt. R. Ballard), Los Angeles Air Force
Station, Los Angeles, California 90045

National Bureau of Standards (Dr. W. J. Hamer), Washington,
D. C. 20234

Director, Defense Documentation Center, Cameron Station, Alexandria,
Virginia 22314 (20 copies)

Aerospace Corporation (Library Acquisition Group), P. O. Box 95085,
Los Angeles, California 90045

American Cyanamid Company (Dr. R. A. Haldeman), 1937 W. Main Street,
Stamford, Connecticut 06902

AMF, Inc. (Mr. R. A. Knight), 689 Hope Street, Stamford,
Connecticut 06902

American University, Chemistry Department (Dr. R. R. Foley),
Massachusetts & Nebraska Avenues, N. W., Washington, D. C. 20016

Atomics International Division, North American Aviation, Inc.
(Dr. H. L. Recht), P. O. Box 309, Canoga Park, California 91304

Autonetics Division, NAR (Mr. R. F. Fogle, GF 18), P. O. Box 4181,
Anaheim, California 92803

Battelle Memorial Institute (Dr. John McCallum), 505 King Avenue,
Columbus, Ohio 43201

Bellcom, Inc. (Mr. J. J. Sakolosky), 955 L'Enfant Plaza, North,
S.W., Washington, D. C. 20024

Bell Telephone Labs, Inc. (Mr. D. O. Feder), Murray Hill,
New Jersey 07974

Dr. Carl Berger, 13401 Kootenay Drive, Santa Ana, California 92705

The Boeing Company (MS 88-06, Mr. Sidney Gross), P. O. Box 3999,
Seattle, Washington 98124

Burgess Battery Division, Gould, Inc. (Mr. M. E. Wilke, Chief
Engineer), Freeport, Illinois 61032

C & D Batteries, Division of Electric Autolite Co. (Dr. Eugene
Willihnganz), 3043 Walton Road, Plymouth Meeting, Pennsylvania 19462

Calvin College (Prof. T. P. Dirkse), 3175 Burton Street, S. E.,
Grand Rapids, Michigan 49506

Catalyst Research Corporation (Mr. F. Tepper), 6308 Blair Hill Lane,
Baltimore, Maryland 21209

Communications Satellite Corp., Comsat Laboratories (Mr. Robert
Strauss), 1835 K Street, N.W., Washington, D. C. 20036

G. & W. H. Corson, Inc. (Dr. L. J. Minnick), Plymouth Meeting,
Pennsylvania 19462

Cubic Corporation (Librarian), 9233 Balboa Avenue, San Diego,
California 92123

Delco-Remy Division, General Motors Corporation (Mr. J. A. Keralla),
2401 Columbus Avenue, Anderson, Indiana 46011

Eagle-Picher Industries, Inc., Couples Department (Mr. E. P.
Broglia), P. O. Box 47, Joplin, Missouri 64801

E. I. du Pont DeNemours & Company, Engineering Materials Laboratory,
Experimental Station (Bldg. 304, Mr. J. M. Williams), Wilmington,
Delaware 19898

ESB, Inc. (Director of Engineering), P. O. Box 11097, Raleigh,
North Carolina 27604

ESB, Inc., Carl F. Norberg Research Center (Dr. Galen Frysinger),
19 West College Avenue, Yardley, Pennsylvania 19067

Electrochimica Corporation (Dr. Morris Eisenberg), 1140 O'Brien
Drive, Menlo Park, California 94025

Electromite Corporation (Mr. R. H. Sparks), 2117 South Anne Street,
Santa Ana, California 92704

Enhart Corporation (Dr. W. P. Cadogan), Box 1620, Hartford,
Connecticut 06102

Energetics Science, Inc. (Dr. H. C. Oswin), 4461 Bronx Boulevard,
New York, New York 10470

Energy Research Corporation (Mr. Martin Klein), 15 Durant Avenue,
Bethel, Connecticut 06801

Dr. Arthur Fleischer, 466 South Center Street, Orange,
New Jersey 07050

General Electric Company, Research and Development Center
(Dr. R. P. Hamlen), P. O. Box 43, Schenectady, New York 12301

General Electric Company, Space Systems (Mr. K. L. Hanson, Room
M-2700), P. O. Box 8555, Philadelphia, Pennsylvania 19101

General Electric Company, Battery Business Section (Mr. P. R. Voyentzie), P. O. Box 114, Gainesville, Florida 32601

General Electric Company (Whitney Library), P. O. Box 8, Schenectady, New York 12301

General Electric (Mr. David F. Schmidt), 777-14th Street, N.W., Washington, D. C. 20005

Globe-Union, Inc. (Mr. John R. Thomas), P. O. Box 591, Milwaukee, Wisconsin 53201

Globe-Union, Inc. (Dr. Eugene Wissman), 5757 North Green Bay Avenue, Milwaukee, Wisconsin 53201

Gould Ionics, Inc. (Dr. J. E. Oxley), P. O. Box 1377, Canoga Park, California 91304

Grumman Aircraft Engineering Corporation, OAO Project (Mr. Steve J. Gaston, Plant 41), Bethpage, Long Island, New York 11714

Gulton Industries, Battery & Power Sources Division, 212 Durham Avenue, Metuchen, New Jersey 08840

Honeywell, Inc., Livingston Electronic Laboratory (Librarian), Montgomeryville, Pennsylvania 18936

Dr. P. L. Howard, Centreville, Maryland 21617

Hughes Aircraft Corporation (M.S. 524, Bldg. 366, Mr. M. E. Ellion), El Segundo, California 90245

ITT Research Institute (Dr. H. T. Francis), 10 West 35th Street, Chicago, Illinois 60616

Idaho State University, Department of Chemistry (Dr. G. Myron Arcand), Pocatello, Idaho 82301

Institute for Defense Analyses (Mr. R. Hamilton), 400 Army-Navy Drive, Arlington, Virginia 22202

Institute for Defense Analyses (Dr. R. Briceland), 400 Army-Navy Drive, Arlington, Virginia 22202

International Nickel Company (Mr. N. A. Matthews), 1000-16th Street, N.W., Washington, D. C. 20036

Johns Hopkins University, Applied Physics Laboratory (Mr. Richard E. Evans), 8621 Georgia Avenue, Silver Spring, Maryland 20910

Leesona Moos Laboratories (Dr. A. Moos), Lake Success Park, Community Drive, Great Neck, New York 11021

Life Systems, Inc. (Dr. Richard A. Wynveen, Pres.), 23715 Mercantile Road, Cleveland, Ohio 44122

Arthur D. Little, Inc. (Dr. James D. Birkett), Acorn Park, Cambridge, Massachusetts 02140

Lockheed Aircraft Corporation (Bldg. 157, Dept. 62-25, Mr. Robert E. Corbett), P. O. Box 504, Sunnyvale, California 94088

Mallory Battery Company (Mr. R. R. Clune), So. Broadway and Sunnyside Lane, Tarrytown, New York 10591

P. R. Mallory and Co., Inc. (Dr. Per Bro), Northwest Industrial Park, Burlington, Massachusetts 01801

P. R. Mallory and Co., Inc. (Library), P. O. Box 1115, Indianapolis, Indiana 46206

Marathon Battery Company (Mr. Lou Belove), Kemble Avenue, Cold Spring, New York 10516

Martin-Marietta Corporation (M.S. 1620, Mr. William B. Collins & M.S. F8845, Mr. M. S. Imamura), P. O. Box 179, Denver, Colorado 80201

Mauchly Associates, Inc. (Dr. John Mauchly), Commerce and Enterprise, Montgomeryville, Pennsylvania 18936

McDonnell Douglas Astronautics Company (MS 17, BBCO, Mr. A. D. Tonelli), 5301 Bolsa Avenue, Huntington Beach, California 92647

McDonnell Douglas Astronautics Company, Headquarters Space Systems Center (Bldg 11-3-12, MS 12, Dr. George Moe), 5301 Bolsa Avenue, Huntington Beach, California 92647

North American Rockwell Corp., Rocketdyne Division (Library), 6633 Canoga Avenue, Canoga Park, California 91304

Philco-Ford Corporation, Power and Control Engineering Department (M.S. R-26, Mr. D. C. Briggs), 3939 Fabian Way, Palo Alto, California 94303

Portable Power Sources Corporation (Mr. Leon Schulman),
166 Pennsylvania Avenue, Mt. Vernon, New York 10552

Power Information Center, University City Science Institute,
Room 2210, 3401 Market Street, Philadelphia, Pennsylvania 19104

Prime Battery Corporation, 15600 Cornet Street, Santa Fe Springs,
California 90670

RAI Research Corporation, 225 Marcus Boulevard, Hauppauge, New
York 11787

RCA Corporation, Astro Electronics Division (Mr. Paul Nekrasov),
P. O. Box 800, Princeton, New Jersey 08540

SAFT Corporation of America (Mr. D. Verrier), 50 Rockefeller Plaza,
New York, New York 10020

Dr. Robert C. Shair, 58 Harman Road, Edison, New Jersey 08817

Southwest Research Institute (Library), P. O. Drawer 28510,
San Antonio, Texas 78228

Spectrolab, Inc. (Dr. Harvey Seiger), 12484 Gladstone Avenue,
Sylmar, California 91342

Stanford Research Institute (Dr. Fritz R. Kalhammer),
19722 Jamboree Boulevard, Irvine, California 92664

Texas Instruments, Inc. (Dr. J. W. Ross), 34 Forest Street,
Attleboro, Massachusetts 02703

TRW Systems, Inc. (Dr. W. R. Scott, M-2/22154), One Space Park,
Redondo Beach, California 90278

TRW Systems, Inc. (Dr. Herbert P. Silverman, R-1/2094), One Space
Park, Redondo Beach, California 90278

TRW, Inc. (Librarian, TIM 3417), 23555 Euclid Avenue, Cleveland,
Ohio 44117

Tyco Laboratories, Inc. (Dr. Jose Giner), Bear Hill, Hickory Drive,
Waltham, Massachusetts 02154

Union Carbide Corporation, Development Laboratory, P. O. Box 6056,
Cleveland, Ohio 44101

Union Carbide Corporation, Consumer Products Division, (Dr. Ralph Brodd), P. O. Box 6116, Cleveland, Ohio 44101

Union Carbide Corporation, Consumer Products Division (Dr. Robert Powers), P. O. Box 6116, Cleveland, Ohio 44101

University of Pennsylvania, Electrochemistry Laboratory
(Prof. John O'M. Bockris), Philadelphia, Pennsylvania 19104

Utah Research and Development Co., Inc. (Mr. William Boyd),
1820 South Industrial Road, Salt Lake City, Utah 84104

Westinghouse Electric Corporation, Research and Development Center
(Dr. C. C. Hein, Contract Admin.), Churchill Borough, Pittsburg,
Pennsylvania 15235

Whittaker Corporation, Power Sources Division (Mr. L. K. White),
3850 Olive Street, Denver, Colorado 80237

Yardney Electric Co. (Mr. P. Deluca and Mr. M. Read), 82 Mechanic
Street, Pawcatuck, Connecticut 02891